

3375.** RING TERMINALS · WITH INSULATION SUPPORT



Specification 8.6 mm Plate

Description Antiturn

Ø (mm) 4,3

Wire size mm² (AWG) 0,75-2 (18-14)

Ø Insulation (mm) 2,5-3,5

Materials, temperature and contact resistance

Material thickness (mm) 0,5

Application tool MN3375

Wire strip length 4.7 (±0.5) mm

Part nr.	Material	Finishing	Max. Temp. (°C)
3375.00	Brass	Natural	110
3375.02	Brass	Tin plated	120
3375.24	Steel	Nickel-plated	300

Crimping parameters & pull out force

Wire section (±10%)	Conductor		Insulator	Pull-out force (N)
	Height (mm)	Width (mm)	Width (mm)	
0.75 mm ²	1.60 (±0.05)	3.25 (±0.05)	4.17 (±0.10)	84N @ 60s
1.00 mm ²	1.65 (±0.05)	3.26 (±0.05)	4.19 (±0.10)	108N @ 60s
1.50 mm ²	1.75 (±0.05)	3.27 (±0.05)	4.19 (±0.10)	150N @ 60s
2.00 mm ²	1.90 (±0.05)	3.28 (±0.05)	4.19 (±0.10)	150N @ 60s

Values only valid for the application tool specified upwards. The insulator widths are only indicative as they are dependent on the sheath thickness of the wire used.

Winding number 7000

Approved regulations

Part nr.	Approval	Standard	File	Certified framework
3375.00	UL	UL 486A-486B	E232316	AWG 18-14 (16-41 Stranded Cu) / MN3375
3375.02	UL	UL 486A-486B	E232316	AWG 18-14 (16-41 Stranded Cu) / MN3375
3375.24	UL	UL 486A-486B	E232316	AWG 18-14 (16-41 Stranded Cu) / MN3375




Approvals



3375.** RING TERMINALS · WITH INSULATION SUPPORT



Drawing



Disclaimer

Data obtained from Escubedo Laboratory essays, using own methodology, cablings, equipment and original crimping tools, done in laboratory conditions and following the indicated standards, errors and omissions excepted. This document has no contractual meaning and it is publicised only for informative purposes. It can be changed without prior notice. The end customer has the sole responsibility to check these characteristics in its environment and with its own components, manufacturing methods and equipment. See also the full range product overview if available. For further information please visit our web site or contact us

Rev. Nr.	Concept	Date	Created/Revised	Approved
A3	Crimping parameters updated	2022-09-20	E.Roura (laboratory dept.)	M.Codina (engineering dept.)
A2	Change company name and logo	2021-10-21	Laboratory Dept.	E. Roura
A1	Datasheet generated automatically [A1]	2018-10-01	Laboratory Dept.	E. Roura